

PELLE REVERSE

REVERSE LEATHER



Beige 01513



Alabastro 01515



Corda 01517



Fango 03513



Argento 08512



Carbone 08513



Salvia 06505



Terra 03518




Caffè 03524



Carminio 04507



Mirtillo 07512



Inchistro 08502

La pelle scamosciata di origine bovina, lavorata sul groppone, viene sottoposta a un processo di concia al cromo e riconcia, seguito da una tintura all'anilina passante e infine da una fase di smerigliatura. Per ottenere questo materiale si utilizza la crosta, ossia la parte interna 'meno nobile' del derma dell'animale, al fine di conferire al pellame un effetto setoso e vellutato. Le pelli scamosciate si confermano in ogni caso pellami di grande pregio.

Suede leather of bovine origin, processed on the rump, undergoes a chrome tanning and retanning process, followed by a pass-through aniline dyeing and finally a buffing phase. This material is obtained using the split leather, which is the inner, less noble part of the animal's hide, to give the leather a silky and velvety effect. Suede leathers are, in any case, considered high-quality materials.